

Product Description

A bauxite based, coarse grained, low cement castable specifically developed for aluminium contact applications. Albond HS has an enhanced strength profile with improved abrasion and thermal shock resistance and provides excellent resistance to corundum growth.

Properties	Albond HS
Region of Manufacture	Europe
Bond Type	Hydraulic
Method of application	Cast
Maximum Service Temperature, °C (°F)	1400 (2550)
Estimated weight of dry material/ m ³ of construction, kg (lb)	2890 (180.4)
Water addition, % by weight	4.7-5.2
Maximum grain size, mm	8
Packaging in bags, kg (lb)	25 (55)

The product(s) represented are intended for industrial refractory applications. The values and application information in this datasheet are given for guidance only. The values and the information given are subject to normal manufacturing variation and may be subject to change without notice. Morgan Advanced Materials – Thermal Ceramics makes no guarantees and gives no warranties about the suitability of a product, and you should seek advice to confirm the product's suitability for use with Morgan Advanced Materials.

Albond[®] HS

Product Data Sheet



Density, kg/m ³ (pcf), ASTM C134	
oven dried, 110°C (230°F)	2920 (182.2)
Cold crushing strength, MPa (psi), ASTM C133	
oven dried, 110°C (230°F)	120-160 (17400-23200)
after 5 hours firing, 1000°C (1832°F)	160-200 (23200-29000)
Permanent linear change, %, ASTM C113	
after 5 hours, 1000°C (1832°F)	-0.25
after 5 hours, 1400°C (2550°F)	0.7
Thermal conductivity, W/m•k (BTU•in./hr•ft ² •°F), ASTM C201/417	
600°C (1112°F)	2.3 (15.96)
Chemical composition, %	
Alumina, Al ₂ O ₃	81
Silica, SiO ₂	11.5
Ferric oxide, Fe ₂ O ₃	1.2
Calcium oxide, CaO	2.6

Storage and Shelf Life

- Should be stored in dry conditions, unopened packaging on pallets. Do not store on ground. Keep out of rain and damp conditions.
- Shelf life is of twelve months with original packaging, double shrink film and dehydrating agent provided if the monolithic is stored under these recommended conditions.

The product(s) represented are intended for industrial refractory applications. The values and application information in this datasheet are given for guidance only. The values and the information given are subject to normal manufacturing variation and may be subject to change without notice. Morgan Advanced Materials – Thermal Ceramics makes no guarantees and gives no warranties about the suitability of a product, and you should seek advice to confirm the product's suitability for use with Morgan Advanced Materials.